



Sede Legale e amministrativa:
 via Bresciani 16
 46040 Gazoldo degli Ippoliti
 Mantova-Italy
 Tel. +39 - 0376 685 1
 Fax. +39 - 0376 685 600
 www.marcegaglia.com

Type 2.2 ATTEST.CONTROLLO v.1
 Number 10418705217
 Issued On 21/11/2018

Customer
TETO EOOD
 BYLGARSKA LEGIYA 36
 1000 SOFIA BG

Consignee
TETO EOOD
 BYLGARSKA LEGIYA 36
 1000 SOFIA BG

Delivery Nn	8304834149	Quality Control	Pages 1/1
Of	21/11/2018	Q.M.D. M.Manaresi	
Delivery note nr	1004052641	Plant Of Ravenna	

Identification Nr	Quantity	Heat	Rm [N/mm	A (%)	1 (µm)	2 (60')	3 (AE)	4	11	6	7
			270	18							
			500								

CPM CPM 0.50X1250.00 DX51D M5305 MARRONE ROSSO-RAL 8012 MP3 POLIESTERE Z 100 EN10169 1181108307/40 MAIL DEL 24/9/18 Date 24/09/2018

18RB139188	3.574 T/M	814188A02	369.6	30.2	22	26	.37	F	100	9	.0
18RB139189	3.414 T/M	814188A02	369.6	30.2	22	26	.37	F	100	9	.0
18RB139191	3.414 T/M	814188A02	369.6	30.2	22	26	.37	F	100	9	.0
18RB139200	3.855 T/M	814188A02	369.6	30.2	22	26	.37	F	100	9	.0
18RB139207	3.936 T/M	A118122	361.6	31.9	22	25	.30	F	100	9	.0
18RB139210	4.046 T/M	A118122	361.6	31.9	22	25	.30	F	100	9	.0
18RB139216	4.046 T/M	A118122	361.6	31.9	22	25	.30	F	100	9	.0
18RB139224	4.036 T/M	A118122	361.6	31.9	22	25	.30	F	100	9	.0
18RB139228	3.916 T/M	A118122	361.6	31.9	22	25	.30	F	100	9	.0
18RB139233	3.825 T/M	1813386	362.1	31.9	22	25	.30	F	100	9	.0
18RB139234	3.825 T/M	1813386	362.1	31.9	22	25	.30	F	100	9	.0
18RB139244	3.765 T/M	1813386	362.1	31.9	22	25	.30	F	100	9	.0

CPM CPM 0.50X1250.00 DX51D M43109 ROSSO 3011 PR. MP3 POLIESTERE Z 100 EN10169 1181108307/50 MAIL DEL 24/9/18 Date 24/09/2018

18RB139167	3.584 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0
18RB139168	3.634 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0
18RB139169	3.634 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0
18RB139171	3.634 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0
18RB139175	3.494 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0
18RB139181	3.213 T/M	836428A01	371.3	29.6	23	27	.40	F	100	9	.0

Remarks:

Document validated acc. EN10204 par. 5
 EN13523-1 Thickness of coating (µ)
 EN13523-2 Specular gloss
 EN13523-3 Instrumental measure
 EN13523-4 Pencil hardness
 EN13523-11 Solvent resistance
 EN13523-6 Adherence after drawing
 EN13523-7 Bend resistance (T)