



Sede Legale e amministrativa:
 via Bresciani 16
 46040 Gazoldo degli Ippoliti
 Mantova-Italy
 Tel. +39 - 0376 685 1
 Fax. +39 - 0376 685 600
 www.marcegaglia.com

Type 2.2 ATTEST.CONTROLLO v.1
 Number 10419185105
 Issued On 05/03/2019

Customer
TETO EOOD
 BYLGARSKA LEGIYA 36
 1000 SOFIA BG

Consignee
TETO EOOD
 BYLGARSKA LEGIYA 36
 1000 SOFIA BG

Delivery Nn	8304905745	Quality Control	Pages 1/1
Of	05/03/2019	Q.M.D. M.Manaresi	
Delivery note nr	1004010109	Plant Of Ravenna	

Identification Nr	Quantity	Heat	Rm [N/mm	A (%)	1 (µm)	2 (60')	3 (AE)	4	11	6	7
			270	18							
			500								

CPM CPM 0.50X1250.00 DX51D M5374 MARRONE CIOCCOLATO P. MP3 POLIESTERE Z 100 EN10169 1181108307/30 MAIL DEL 24/9/18 Date 24/09/2018

19RB006308	2.289 T/M	SI41832	361.6	31.6	22	25	.30	F	100	9	.0
19RB011939	3.695 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011941	3.795 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011942	3.795 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011943	3.795 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011945	3.896 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011947	3.875 T/M	43919I	364.1	31.0	22	26	.33	F	100	9	.0
19RB011950	4.106 T/M	43943I	363.6	31.5	22	25	.31	F	100	9	.0
19RB011957	4.106 T/M	43943I	363.6	31.5	22	25	.31	F	100	9	.0
19RB011963	4.106 T/M	43943I	363.6	31.5	22	25	.31	F	100	9	.0

CPM CPM 0.50X1250.00 DX51D M1305 BIANCO FUMO-RAL 9002 MP3 POLIESTERE Z 100 EN10169 1181108307/60 MAIL DEL 24/9/18 Date 24/09/2018

19RB013599	4.264 T/M	811876	368.0	30.3	22	26	.37	F	100	9	.0
19RB013606	3.346 T/M	811876	368.0	30.3	22	26	.37	F	100	9	.0
19RB013612	4.304 T/M	811876	368.0	30.3	22	26	.37	F	100	9	.0
19RB013639	4.082 T/M	811876	368.0	30.3	22	26	.37	F	100	9	.0
19RB013648	3.77 T/M	811876	368.0	30.3	22	26	.37	F	100	9	.0

Remarks:

Document validated acc. EN10204 par. 5
 EN13523-1 Thickness of coating (µ)EN13523-2 Specular glossEN13523-3 Instrumental
 measureEN13523-4 Pencil hardnessEN13523-11 Solvent resistanceEN13523-6 Adherence
 after drawingEN13523-7 Bend resistance (T)