

Customer
TETO EOOD
BYLGARSKA LEGIYA 36
1000 SOFIA BG

Consignee
Teto EOOD
bul. Ilievtzi 12
1000 Sofia BG

Delivery Nn	8304722387	Quality Control	Pages 1/1
Of	23/08/2017	Q.M.D. M.Manaresi	
Delivery note nr	1004035742	Plant Of Ravenna	

Identification Nr	Quantity	Heat	Rm [N/mm	A (%)	1 (µm)	2 (60')	3 (AE)	4	11	6	7
			270	18							
			500								

CPM CPM 0.50X1250.00 DX51D Z 100 MP3 POLIESTERE M5305 MARRONE ROSSO-RAL 8012 EN10169 1171083467/20 -- Date 25/05/2017

17RB100453	3.956 T/M	373651	360.3	31.6	22	25	.30	F	100	9	.0
17RB100454	3.946 T/M	373651	360.3	31.6	22	25	.30	F	100	9	.0
17RB100455	4.006 T/M	373651	360.3	31.6	22	25	.30	F	100	9	.0
17RB100456	3.996 T/M	373651	360.3	31.6	22	25	.30	F	100	9	.0
17RB100458	3.996 T/M	373651	360.3	31.6	22	25	.30	F	100	9	.0

CPM CPM 0.50X1250.00 DX51D Z 100 MP3 POLIESTERE M5305 MARRONE ROSSO-RAL 8012 EN10169 1171083467/40 -- Date 25/05/2017

17RB100450	4.327 T/M	792853	360.6	31.8	22	25	.30	F	100	9	.0
17RB100461	3.614 T/M	792853	360.6	31.8	22	25	.30	F	100	9	.0
17RB100462	3.414 T/M	792853	360.6	31.8	22	25	.30	F	100	9	.0
17RB100463	3.464 T/M	792853	360.6	31.8	22	25	.30	F	100	9	.0

Remarks:

Document validated acc. EN10204 par. 5
EN13523-1 Thickness of coating (µ)
EN13523-2 Specular gloss
EN13523-3 Instrumental measure
EN13523-4 Pencil hardness
EN13523-11 Solvent resistance

EN13523-6 Adherence after drawing
EN13523-7 Bend resistance (T)